

# CELLTEX LTD

UNIT 9A, RAMSAY ROAD, BARNFIELD INDUSTRIAL ESTATE, TIPTON, WEST MIDLANDS, DY4 9DU

Tel: 0121 520 3443 Fax: 0121 520 1772 Website: [www.celltex.co.uk](http://www.celltex.co.uk) Email: [sales@celltex.co.uk](mailto:sales@celltex.co.uk)

*Closed Cell Foam and Rubber for the Construction and Acoustic Industries*

## DATA SHEET

### Grout Check Tape

	ISO Standard	Unit	
Density	ISO - 845	kg/m <sup>3</sup>	33
Tensile Strength			
Lengthwise	ISO – 1798	kPa	395
Crosswise	ISO – 1798	kPa	250
Tensile Elongation			
Lengthwise	ISO – 1798	%	140
Crosswise	ISO – 1798	%	120
Compressive Strength			
Deflection 10%	ISO – 844	kPa	19
Deflection 25%	ISO – 844	kPa	38
Deflection 50%	ISO – 844	kPa	105
Compression Set 25% comp	ISO – 1856	%	
½ hr recovery			21
24hr recovery			12
Working Temperature Range	Internal	°C	-80 / +100
Water Absorption (7 days) (Vol) <1	Internal	%	<1%