

# TEXELL 3

## Movement Joint Filler



### Features

- For use in brick and blockwork
- Low water absorption
- Meets BS & DOT specifications
- Rot proof
- CFC free

### Uses

Texell 3 is a white coloured, closed cell, non-cross-linked, polyethylene, low resistance joint filler, for use in brick and blockwork. It fully meets the specification of BS5628 Pt 3: 2001 Section 5.4.3 – Code of Practice for use of masonry.

Texell 3 is ozone, oil, and weather resistant, and has very low water absorption properties of <1% by volume.

Where Texell 3 is used as a joint filler, there is no need for any additional bond breaker.

### Joint Detail

In general terms the size/width of the joint should be double the expected total movement, allowing for the compressibility of both the filler and the mastic.

### Technical Data

Density	ISO 845	Av 28kg/m <sup>3</sup>
Compressive Strength		
25%	DIN53577	0.028N/mm <sup>2</sup>
50%		0.083N/mm <sup>2</sup>
75%		0.200N/mm <sup>2</sup>
Compression Set		
22h Charge 23°C	ASTM D3575-08	
Deflection 50%		
½ hr recovery		10%
Tensile Strength	ISO 1798	150kPa
Elongation at Break	ISO 1798	52%
Tear Resistance	DIN 53575	17N/cm
Thermal Conductivity	ASTM C177	0.055W/mK
Water Absorption	DIN 53428	
24hours immersion		2% by volume

### Sizes Available

#### Strip:

10, 12, 15mm available in 10mt rolls  
20, 25mm available in 2mt lengths

#### Sheets:

10, 12, 15, 20, 25mm  
available in 2mt x 1.2mt

Other thicknesses are available upon request

# CELLTEX LTD

Unit 9a, Ramsay Road  
Barnfield Industrial Estate  
Tipton, West Midlands, DY4 9DU

Tel: +44 (0) 121 520 3443  
Fax: +44 (0) 121 520 1772

Email: [sales@celltex.co.uk](mailto:sales@celltex.co.uk)  
[www.celltex.co.uk](http://www.celltex.co.uk)