

CELLTEX LTD

UNIT 12 BLOCK 3, WEDNESBURY TRADING ESTATE, WEDNESBURY WS10 7JN

Tel: 0121 520 3443 Website: www.celltex.co.uk Email: sales@celltex.co.uk

Closed Cell Foam and Rubber for the Construction and Acoustic Industries

DATA SHEET

TEXELL 3 - S

	ISO Standard	Unit	
Density	ISO - 845	kg/m ³	30
Tear Strength @ Peak (MD/CD)	ISO - 1798	kPa	200
Tensile Elongation (MD/CD)	ISO – 1798	%	65
Tear Strength (MD/CD)	ASTM D3575-08	n/cm	17 / 18
Thermal Stability (24 hours at 70°C)	ISO – 2796	%	<2
Compressive Strength			
25% (4 th compression)	DIN 53577	kPa	30
50% (4 th compression)	DIN 53577	kPa	90
75% (4 th compression)	DIN 53577	kPa	205
Compression Set			
Deflection 50%			
0.5 h after discharge	ASTM D3575-08	%	<10
Water Absorption (24 hours)	ISO - 2896	Volume %	<3
Cell size	BS 4443/1 Met 4	Cells/25mm	≥26
Thermal Conductivity	ASTM C177	W/mK	0.05
Fire-test response Characteristics (1)	FMVSS 302		Pass
Transportation			
Automotive			

- Data represents typical values for an unfabricated polyethylene foam product, and as such should be considered as a guideline only.